

NX-02BK

PA6

Next Polymers Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.013	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.013	mm/mm	ASTM D 955
Mechanical properties	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	65 / 55	MPa	ASTM D 638
Elongation at Break	20 / 110	%	ASTM D 638
Flexural Modulus	2600 / 2100	MPa	ASTM D 790
Flexural Strength	95 / 90	MPa	ASTM D 790
Rockwell Hardness	R 110 /	-	ASTM D 785
Izod Impact notched, 1/8 in	58.9 / 78.5	J/m	ASTM D 256
Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	175	°C	ASTM D 648
DTUL @ 264 psi	70	°C	ASTM D 648
Melting Temperature	220	°C	ASTM D 3418
Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Electric strength	30 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112
Other properties	Value	Unit	Test Standard
Water Absorption, 24hr	2.4	%	ASTM D 570
Water Absorption, Equilibrium	6.5	%	ASTM D 570
Density	1130	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Applications

Electrical and Electronical

Delivery form

Black

Regional Availability

Asia Pacific