

NYLEM 6 FR V0

PA6

Emas Plastik San.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.0	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2100	MPa	ISO 527
Tensile Strength	55	MPa	ISO 527
Strain at break	15	%	ISO 527
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
Shore D hardness	78	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	85	°C	ISO 75-1/-2
Vicat softening temperature, B	215	°C	ISO 306
Burning behav. at thickness h	V-0	class	IEC 60695-11-10

Other properties	Value	Unit	Test Standard
Density	1200	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	250 - 300	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Regional Availability

Europe, Near East/Africa

Special Characteristics

Flame retardant