

Product Texts

Orgalloy® LE 60 THM NAT resin is a polyamide alloy especially designed for tube and profile extrusion. This natural grade dedicated to extrusion offers excellent barrier properties and chemical resistance to hydrocarbons, alcohols and solvents while exhibiting a good cold impact performance and abrasion resistance. Conform to the European regulations concerning materials in contact with foodstuffs.

Main applications:

- Fuel station pipes
- barrier layer to hydrocarbons and alcohols
- Guidance tubing for cars sunroof
- Cable protection profiles resistant to hydrocarbons
- MLT fuel lines containing alcohols
- Food and chemical packaging
- Slide rails & rolls for conveyor industry
- Profiles

Packaging:

This grade is delivered dried in sealed packaging (25kg bags) ready to be processed.

Shelf life:

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	3.8 / *	cm ³ /10min	ISO 1133
Temperature	235 / *	°C	-
Load	2.16 / *	kg	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2000 / 1800	MPa	ISO 527
^[C] Yield stress	49 / 42	MPa	ISO 527
^[C] Yield strain	4 / 5	%	ISO 527
^[C] Nominal strain at break	>50 / >50	%	ISO 527
^[C] Tensile creep modulus, 1h	* / 1520	MPa	ISO 899-1
^[C] Tensile creep modulus, 1000h	* / 690	MPa	ISO 899-1
^[C] Charpy notched impact strength, +23°C	23 / 26	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12 / 12	kJ/m ²	ISO 179/1eA
^[C] Shore D hardness	68 / *	-	ISO 7619-1

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	48 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	86 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	131 / *	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.2 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Surface resistivity	* / >1E15	Ohm	IEC 62631-3-2
^[C] Comparative tracking index	* / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	6.5 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.4 / *	%	Sim. to ISO 62
^[C] Density	1050 / 1050	kg/m ³	ISO 1183

[C]: CAMPUS

Film Properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Stress at yield, parallel	35 / *	MPa	ISO 527-3
^[C] Stress at yield, normal	35 / *	MPa	ISO 527-3
^[C] Strain at yield, parallel	16 / *	%	ISO 527-3
^[C] Strain at yield, normal	16 / *	%	ISO 527-3
^[C] Maximum stress, parallel	61 / *	MPa	ISO 527-3
^[C] Maximum stress, normal	55 / *	MPa	ISO 527-3
^[C] Maximum strain, parallel	610 / *	%	ISO 527-3
^[C] Maximum strain, normal	550 / *	%	ISO 527-3
^[C] Elmendorf Tear resistance, parallel	45 / *	N	ISO 6383-2
^[C] Elmendorf Tear resistance, normal	55 / *	N	ISO 6383-2

[C]: CAMPUS

Characteristics

Processing

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion, Calandring, Transfer Molding, Thermoforming

Delivery form

Pellets, Natural Color

Special Characteristics

Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Other extrusion

Processing conditions:

- Drying time (only necessary for bags opened for more than two hours): 4-8 hours at 80°C
- Extrusion melt temperature (min-recommended-max): 250-260-270°C