

PA ECOTAN B HI FL GRIGIO 2512

PA6

Soredi S.p.a.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------------|----------------------|
| ISO Data | | | |
| Molding shrinkage, parallel | 1.5 | % | ISO 294-4, 2577 |
| Mechanical properties | | | |
| ASTM Data | | | |
| Tensile Strength at Break | 50 | MPa | ASTM D 638 |
| Flexural Modulus | 2300 | MPa | ASTM D 790 |
| Flexural Strength | 70 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 101 | J/m | ASTM D 256 |
| Thermal properties | | | |
| ASTM Data | | | |
| UL 94 Flame rating | HB | - | UL 94 |
| Thickness tested | 1.6 | mm | - |
| DTUL @ 264 psi | 60 | °C | ASTM D 648 |
| Vicat Temperature | 170 | °C | ASTM D 1525 |
| Electrical properties | | | |
| ISO Data | | | |
| Electric strength | 18 | kV/mm | IEC 60243-1 |
| Comparative tracking index | 500 | - | IEC 60112 |
| Other properties | | | |
| Water Absorption, 24hr | 8 | % | ASTM D 570 |
| Density | 1100 | kg/m ³ | ASTM D 792 |

Characteristics

Special Characteristics
High impact or impact modified

Regional Availability
Europe