

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Yield stress	80	MPa	ISO 527
Yield strain	4	%	ISO 527
Nominal strain at break	20	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Vicat softening temperature, B	200	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	8.5	%	Sim. to ISO 62
Humidity absorption	2.9	%	Sim. to ISO 62
Density	1140	kg/m ³	ISO 1183

Characteristics

Processing

Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Other Extrusion

Chemical Resistance

General Chemical Resistance

Certifications

Recycled Resin Content

Regional Availability

Europe