

PENTAMID B SK H

PA6

Pentac Polymer GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.6 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	3200 / 1100	MPa	ISO 527
Yield stress	85 / 50	MPa	ISO 527
Yield strain	4 / 15	%	ISO 527
Flexural modulus, 23°C	3100 / -	MPa	ISO 178
Flexural strength	115 / -	MPa	ISO 178
Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8 / 22	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	170 / *	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-

Other properties	dry / cond	Unit	Test Standard
Water absorption	9 / *	%	Sim. to ISO 62
Humidity absorption	3.4 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m ³	ISO 1183

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	145 / *	cm ³ /g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	3	h	-
Processing humidity	≤0.13	%	-
Mold temperature	60 - 100	°C	-
Feed temperature	80	°C	-
Zone 1	260	°C	-
Zone 2	270	°C	-
Zone 3	275	°C	-
Zone 4	280	°C	-
Zone 5	275	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Certifications

RoHS compliant

Applications

Encapsulation

Features

Nucleated

Regional Availability

Europe