

PRL NY6-GP1-(color)H

PA6

Polymer Resources, Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.013	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	75.8	MPa	ASTM D 638
Tensile Strength at Break	75.8	MPa	ASTM D 638
Flexural Modulus	2758	MPa	ASTM D 790
Flexural Strength	106	MPa	ASTM D 790
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	177	°C	ASTM D 648
DTUL @ 264 psi	65.6	°C	ASTM D 648
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	29.1	kV/mm	ASTM D 149
Volume Resistivity	1E11	Ohm*cm	ASTM D 257
Other properties			
Density	1130	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	73.9 - 85	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	238 - 279	°C	-
Mold temperature	65.6 - 82.2	°C	-
Zone 1	221 - 246	°C	-
Zone 2	238 - 254	°C	-
Zone 3	243 - 260	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets

Applications

General Purpose

Additives

Lubricants

Regional Availability

North America