

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>78</b>	g/10min	ISO 1133
Temperature	<b>275</b>	°C	-
Load	<b>5</b>	kg	-
Molding shrinkage, parallel	<b>0.4</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>0.5</b>	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>3000</b>	MPa	ISO 527
Yield stress	<b>95</b>	MPa	ISO 527
Stress at break	<b>96</b>	MPa	ISO 527
Strain at break	<b>6</b>	%	ISO 527
Flexural modulus, 23°C	<b>2900</b>	MPa	ISO 178
Flexural strength	<b>120</b>	MPa	ISO 178
Izod impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	<b>3</b>	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Glass transition temperature, 10°C/min	<b>120</b>	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	<b>105</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>115</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>60</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	<b>60</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>V-2</b>	class	IEC 60695-11-10
Burning rate, FMVSS, Thickness 1 mm	<b>100</b>	mm/min	ISO 3795 (FMVSS 302)
Glow Wire Flammability Index (GWFI)	<b>960</b>	°C	IEC 60695-2-12
GWFI - thickness tested (1)	<b>3</b>	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	<b>1E11</b>	Ohm*m	IEC 62631-3-1

Optical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Luminous transmittance	<b>89</b>	%	ISO 13468-1, -2

Other properties	Value	Unit	Test Standard
Density	<b>1180</b>	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>12 - 36</b>	h	-
Processing humidity	<b>≤0.04</b>	%	-
Melt temperature	<b>260 - 290</b>	°C	-
Mold temperature	<b>70 - 90</b>	°C	-

**Characteristics**

**Processing**  
Injection Molding

**Regional Availability**  
Europe

**Features**  
Amorphous