

Novanyl PAX003CZ015

PA*

Plásticos Novacor Ltda

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	80	MPa	ASTM D 638
Flexural Modulus	3000	MPa	ASTM D 790
Flexural Strength	130	MPa	ASTM D 790
Izod Impact notched, 1/8 in	0.3	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1050	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Applications

Automotive