

Novanyl PAX012NC001

PA*

Plásticos Novacor Ltda

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	65	MPa	ASTM D 638
Flexural Modulus	1800	MPa	ASTM D 790
Izod Impact notched, 1/8 in	60	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	163	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

South and Central America

Applications

Automotive