

NYLENE® 203-MS3

PA*

Polymeric Resources Corporation

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	64.1	MPa	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Flexural Modulus	2282	MPa	ASTM D 790
Izod Impact notched, 1/8 in	74.7	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	223	°C	ASTM D 3418

Characteristics**Processing**

Injection Molding

Features

Copolymer

Additives

Lubricants

Regional Availability

North America