

**Product Texts**

**Platamid® H 2513 Powder**

Copolyamide Hot Melt Adhesive / Textile Applications

**Platamid® H 2513 Powder** is a medium melt viscosity copolyamide adhesive powder for the production of fusible interlinings. **Platamid® H 2513 Powder** offers an excellent laundry resistance up to 60°C and an excellent resistance to all kind of steam treatment.

**AVAILABLE GRADES**

This product is available in different grain sizes:

- Platamid® H 2513 PA 80 (0-80 µm paste dot)
- Platamid® H 2513 PTA 170/20 (0-170 µm powder dot)
- Platamid® H 2513 PTA 170 (80-170 µm double dot)

**PACKAGING**

- Platamid® H 2513 PA 80 and Platamid® H 2513 PTA 170/20 are delivered in 20 kg sealed bags.

- Platamid® H 2513 PTA 170 is delivered in 20 kg sealed bags and 500 kg sealed big bags (GRVS).

**SHELF LIFE**

Two years from the date of delivery. For any use above this limit, please refer to our technical services.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>30 / *</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>160 / *</b>	°C	-
Load	<b>2.16 / *</b>	kg	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>128 / *</b>	°C	ISO 11357-1/-3

[C]: CAMPUS

**Characteristics**

**Delivery form**

Powder

**Features**

Copolymer

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa