

## Product Texts

PA,,MHT,C14-020

Rilsan® Clear G820 Rnew® is a high performance transparent polyamide with outstanding chemical resistance and stress cracking resistance. This grade has been designed for injection molding applications.

According to ASTM D6866, the biobased carbon content is measured at 62%.

## Main applications:

- Optic
- Electronics
- Domestic appliances

## Packaging:

This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

## Shelf Life:

Two years from the delivery. For any use above this limit, please refer to our technical services.

| Processing/Physical Characteristics        | dry / cond | Unit                   | Test Standard   |
|--|------------|------------------------|-----------------|
| <b>ISO Data</b>                            |            |                        |                 |
| <sup>[C]</sup> Melt volume-flow rate, MVR  | 8 / *      | cm <sup>3</sup> /10min | ISO 1133        |
| Temperature                                | 275 / *    | °C                     | -               |
| Load                                       | 2.16 / *   | kg                     | -               |
| <sup>[C]</sup> Molding shrinkage, parallel | 0.6 / *    | %                      | ISO 294-4, 2577 |
| <sup>[C]</sup> Molding shrinkage, normal   | 0.7 / *    | %                      | ISO 294-4, 2577 |

[C]: CAMPUS

| Mechanical properties                                | dry / cond | Unit              | Test Standard |
|--|------------|-------------------|---------------|
| <b>ISO Data</b>                                      |            |                   |               |
| <sup>[C]</sup> Tensile Modulus                       | - / 1665   | MPa               | ISO 527       |
| <sup>[C]</sup> Yield stress                          | - / 66     | MPa               | ISO 527       |
| <sup>[C]</sup> Yield strain                          | - / 7      | %                 | ISO 527       |
| <sup>[C]</sup> Nominal strain at break               | - / >50    | %                 | ISO 527       |
| <sup>[C]</sup> Charpy notched impact strength, +23°C | - / 6      | kJ/m <sup>2</sup> | ISO 179/1eA   |
| <sup>[C]</sup> Charpy notched impact strength, -30°C | - / 9      | kJ/m <sup>2</sup> | ISO 179/1eA   |
| <sup>[C]</sup> Shore D hardness                      | 76 / *     | -                 | ISO 7619-1    |

[C]: CAMPUS

| Thermal properties                                      | dry / cond | Unit | Test Standard  |
|---|------------|------|----------------|
| <b>ISO Data</b>   |            |      |                |
| <sup>[C]</sup> Glass transition temperature, 10°C/min   | 101 / *    | °C   | ISO 11357-1/-2 |
| <sup>[C]</sup> Temp. of deflection under load, 1.80 MPa | 73 / *     | °C   | ISO 75-1/-2    |
| <sup>[C]</sup> Temp. of deflection under load, 0.45 MPa | 85 / *     | °C   | ISO 75-1/-2    |

[C]: CAMPUS

| Other properties                   | dry / cond  | Unit              | Test Standard  |
|------------------------------------|-------------|-------------------|----------------|
| <sup>[C]</sup> Water absorption    | 2.45 / *    | %                 | Sim. to ISO 62 |
| <sup>[C]</sup> Humidity absorption | 1.16 / *    | %                 | Sim. to ISO 62 |
| <sup>[C]</sup> Density             | 1000 / 1000 | kg/m <sup>3</sup> | ISO 1183       |
| Biobased content                   | 60          | %                 | -              |

[C]: CAMPUS

| <b>Processing Recommendation Injection Molding</b> | <b>Value</b>     | <b>Unit</b> | <b>Test Standard</b> |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature                           | <b>80</b>        | °C          | -                    |
| Pre-drying - Time                                  | <b>4 - 6</b>     | h           | -                    |
| Melt temperature                                   | <b>260 - 300</b> | °C          | -                    |
| Mold temperature                                   | <b>20 - 80</b>   | °C          | -                    |

**Characteristics**

**Processing**

Injection Molding

**Certifications**

Contains renewable resources

**Delivery form**

Pellets

**Applications**

Electrical and Electronical

**Special Characteristics**

Transparent

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America

**Chemical Resistance**

General Chemical Resistance, Environmental Stress Crack Resistance

**Other text information**

**Injection molding**

**Processing conditions:**

- Typical melt temperature (Min / Recommended / Max) : 260°C / 280°C / 300°C
- Typical mold temperature : 20 - 80 °C
- Drying time and temperature (only for bags opened for more than two hours): 4 - 6 hours at 80°C