

VESTAMID HT plus M3000

PA*

Daicel-Evonik Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.4	%	ISO 294-4, 2577
Molding shrinkage, normal	1.5	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2700	MPa	ISO 527
Stress at break	73	MPa	ISO 527
Strain at break	5	%	ISO 527
Charpy impact strength, +23°C	60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	285	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	125	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	128	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	225	°C	ISO 75-1/-2
Other properties			
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1100	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Chemical Resistance

General Chemical Resistance

Certifications

Food contact, Drinking water contact

Regional Availability

North America, Europe, Asia Pacific, South and Central America