

Promyde® B40

PA6

Nurel S.A.

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Water absorption	9	%	Sim. to ISO 62
Humidity absorption	3	%	Sim. to ISO 62
Density	1130	kg/m ³	ISO 1183
Moisture Content	0.1	%	-

Characteristics**Processing**

Film Extrusion, Other Extrusion

Regional Availability

Europe