

Product Texts

Polyamide 6 impact modified prime quality compound available in custom colors also available heat stabilized (H) and UV stabilized (UV).

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.011	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Yield stress	45	MPa	ISO 527
Stress at break	45	MPa	ISO 527
Strain at break	80	%	ISO 527
Flexural modulus, 23°C	1800	MPa	ISO 178
Izod notched impact strength, +23°C	9	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	5 -30	kJ/m ² °C	ISO 180/1A -
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.6	class mm	IEC 60695-11-10 -
Burning behav. at thickness h Thickness tested	HB 3.2	class mm	IEC 60695-11-10 -
Glow Wire Flammability Index (GWFI)	650	°C	IEC 60695-2-12
GWFI - thickness tested (1)	2	mm	-
Electrical properties			
ISO Data			
Electric strength	18	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112
Other properties			
Density	1080	kg/m ³	ISO 1183
Water Absorption, 24hr	2.5	%	ASTM D 570
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75	°C	-
Pre-drying - Time	3 - 4	h	-
Processing humidity	≤0.12	%	-
Melt temperature	240 - 270	°C	-
Mold temperature	70 - 90	°C	-
Zone 1	220 - 230	°C	-
Zone 2	230 - 245	°C	-
Zone 3	250 - 260	°C	-
Nozzle temperature	250 - 260	°C	-
Screw speed	50 - 80	rpm	-
Back pressure	0.4 - 0.8	MPa	-
Holding pressure	6 - 8	MPa	-

Characteristics

Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

Europe