

RESTRAMID B27 N NT 1A0000

PA6

Polimarky Spółka Jawna

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	- / 2200	MPa	ISO 527
Strain at break	- / 20	%	ISO 527

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	66 / *	°C	ISO 75-1/-2
Vicat softening temperature, A	199 / *	°C	ISO 306

Other properties	dry / cond	Unit	Test Standard
Density	- / 1130	kg/m ³	ISO 1183

Characteristics**Delivery form**

Natural Color

Regional Availability

Europe

Features

Nucleated