

SCHULABLEND® 600

PA6

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Izod Impact notched, 1/8 in	641	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	150	°C	ASTM D 648
Vicat Temperature	160	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	1090	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America