

SCHULAMID® 6 MKF 4014

PA6

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	131	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638

Other properties	Value	Unit	Test Standard
Density	1490	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America