

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	170	cm <sup>3</sup> /10min	ISO 1133
Temperature	275	°C	-
Load	5	kg	-
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
Molding shrinkage, normal	1.4	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	2900	MPa	ISO 527
Yield stress	80	MPa	ISO 527
Yield strain	3.8	%	ISO 527
Flexural modulus, 23°C	2700	MPa	ISO 178
Flexural strength	100	MPa	ISO 178
Charpy notched impact strength, +23°C	4	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	218	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	60	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	165	°C	ISO 75-1/-2
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Comparative tracking index	600	-	IEC 60112
<b>Other properties</b>			
Water absorption	9.7	%	Sim. to ISO 62
Humidity absorption	3.5	%	Sim. to ISO 62
Density	1120	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Regional Availability

North America, Europe