

**Product Texts**

Polyamide 6, for injection moulding

**Processing/Physical Characteristics**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	10	g/10min	ISO 1133
<sup>[C]</sup> Molding shrinkage, parallel	0.9 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.0 / *	%	ISO 294-4, 2577

<sup>[C]</sup>: CAMPUS**Mechanical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	3000 / 1000	MPa	ISO 527
Flexural modulus, 23°C	2650 / 850	MPa	ISO 178
Flexural strength	95 / 30	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	5.5 / 22	kJ/m <sup>2</sup>	ISO 179/1eA

<sup>[C]</sup>: CAMPUS**Thermal properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	70 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	170 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	200 / *	°C	ISO 306
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

<sup>[C]</sup>: CAMPUS**Electrical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2

<sup>[C]</sup>: CAMPUS**Other properties**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1140 / -	kg/m <sup>3</sup>	ISO 1183

<sup>[C]</sup>: CAMPUS**Material specific properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Viscosity number	135 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

**Characteristics****Processing**

Injection Molding