

Product Texts

Polyamide 6, improved flowability, for injection moulding

Processing/Physical Characteristics

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.0 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2900 / -	MPa	ISO 527
Flexural modulus, 23°C	2600 / -	MPa	ISO 178
Flexural strength	100 / -	MPa	ISO 178
^[C] Charpy impact strength, +23°C	N / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Yellow Card available	yes / *	-	-
^[C] Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties

	dry / cond	Unit	Test Standard
^[C] Density	1130 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Material specific properties

	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	135 / *	cm ³ /g	ISO 307, 1157, 1628

Characteristics**Processing**

Injection Molding

Delivery form

Black