

**Product Texts**

Polyamide 6, improved flowability, for injection moulding

**Processing/Physical Characteristics**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	225 / *	cm <sup>3</sup> /10min	ISO 1133
Load	5 / *	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	1.0 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.1 / *	%	ISO 294-4, 2577

[C]: CAMPUS

**Mechanical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	3100 / 1000	MPa	ISO 527
<sup>[C]</sup> Yield stress	80 / 40	MPa	ISO 527
<sup>[C]</sup> Yield strain	4 / 20	%	ISO 527
Flexural modulus, 23°C	2700 / 850	MPa	ISO 178
Flexural strength	100 / 35	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	4 / 20	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	175 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	200 / *	°C	ISO 306
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

**Electrical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E14	Ohm	IEC 62631-3-2
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

**Other properties**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1140 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Material specific properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Viscosity number	125 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

**Characteristics****Processing**

Injection Molding