

**Product Texts**

Polyamide 6, medium viscosity, for injection moulding

**Processing/Physical Characteristics**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	44 / *	cm <sup>3</sup> /10min	ISO 1133
Load	5 / *	kg	-

**Mechanical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2900 / -	MPa	ISO 527
Flexural modulus, 23°C	2700 / -	MPa	ISO 178
Flexural strength	95 / -	MPa	ISO 178
<sup>[C]</sup> Charpy notched impact strength, +23°C	5.5 / -	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

**Thermal properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	70 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	180 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	205 / *	°C	ISO 306
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

**Electrical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

**Other properties**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1140 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Material specific properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Viscosity number	200 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628

**Characteristics****Processing**

Injection Molding, Other Extrusion

**Delivery form**

Natural Color