

**Product Texts**

Genestar GN2330-1 is one of standard grades.

Main feature of GN2300-1 is:

-Good balance of mechanical strength, mold ability, and dimensional stability

Examples of applications are:

-FPC Connectors

-Board to Board / Wire to Board Connectors

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.8	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Melt Flow Index, MFI	21	g/10min	ASTM D 1238
Temperature	320	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Stress at break	184	MPa	ISO 527
<sup>[C]</sup> Strain at break	1.8	%	ISO 527
<sup>[C]</sup> Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
<b>ASTM Data</b>			
Tensile Strength	185	MPa	ASTM D 638
Flexural Modulus	11000	MPa	ASTM D 790
Flexural Strength	240	MPa	ASTM D 790
Izod Impact notched, 1/8 in	100	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	306	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	125	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	285	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
<sup>[C]</sup> Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	V-0	-	UL 94
DTUL @ 264 psi	285	°C	ASTM D 648
Melting Temperature	306	°C	ASTM D 3418
Glass Transition Temperature	125	°C	ASTM E 1356

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Electric strength	30	kV/mm	IEC 60243-1
<b>ASTM Data</b>			
Dielectric Strength, Short Time	30	kV/mm	ASTM D 149
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.13	%	Sim. to ISO 62
Density	1620	kg/m <sup>3</sup>	ASTM D 792

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Features**

Weldable

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa