

Reny 2041

PAMXD6-(GF+MX)40

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	11 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	2.16 / *	kg	-
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	275	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	18300 / 14100	MPa	ISO 527
Stress at break	187 / 136	MPa	ISO 527
Strain at break	1.4 / 1.6	%	ISO 527
Flexural modulus, 23°C	16200 / 12800	MPa	ISO 178
Flexural strength	299 / 230	MPa	ISO 178
Charpy impact strength, +23°C	47 / 54	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6.6 / 7.3	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	214 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	231 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	50 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thckn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	-
Yellow Card available	yes / *	-	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	5 / 5	-	IEC 62631-2-1
Dissipation factor, 1MHz	90 / 380	E-4	IEC 62631-2-1
Volume resistivity	- / 2E11	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 5E12	Ohm	IEC 62631-3-2
Electric strength	22 / 21	kV/mm	IEC 60243-1
Comparative tracking index	500 / 500	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Humidity absorption	1.3 / *	%	Sim. to ISO 62
Density	1700 / -	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	3	h	-
Mold temperature	120 - 140	°C	-
Zone 1	265	°C	-
Zone 2	270	°C	-
Zone 3	275	°C	-
Nozzle temperature	275	°C	-
Screw speed	60 - 150	rpm	-
Injection pressure	20 - 150	MPa	-

Characteristics

Reny 2041

PAMXD6-(GF+MX)40

Mitsubishi Engineering-Plastics Corporation

Processing

Injection Molding

Applications

Automotive, Electrical and Electronical, General Purpose

Regional AvailabilityNorth America, Europe, Asia Pacific, South and Central America,
Near East/Africa