

Titalon X600CF

PAMXD6-CF30

Titan Plastics Compounds Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	240	MPa	ISO 527
Flexural modulus, 23°C	25000	MPa	ISO 178
Flexural strength	350	MPa	ISO 178
Charpy notched impact strength, +23°C	5	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	230	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	100	Ohm*m	IEC 62631-3-1
Surface resistivity	10000	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1360	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	4	h	-
Melt temperature	240 - 270	°C	-
Mold temperature	100 - 130	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Black

Special Characteristics

Increased electrical conductivity, Heat stabilized or stable to heat, Thermally Conductive

Applications

Automotive, Electrical and Electronical

Regional Availability

Asia Pacific