

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Thermal conductivity of melt	1	W/(m K)	-
Mechanical properties			
ISO Data			
Tensile Modulus	28000	MPa	ISO 527
Tensile Strength	360	MPa	ISO 527
Flexural modulus, 23°C	24000	MPa	ISO 178
Charpy impact strength, +23°C	60	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	4	E-6/K	ISO 11359-1/-2
Electrical properties			
ISO Data			
Surface resistivity	10000	Ohm	IEC 62631-3-2
Other properties			
Density	1310	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	100	°C	-
Pre-drying - Time	6 - 8	h	-
Processing humidity	≤0.1	%	-
Melt temperature	285	°C	-
Mold temperature	110 - 140	°C	-
Zone 1	260 - 300	°C	-
Zone 2	260 - 300	°C	-
Zone 3	260 - 300	°C	-
Nozzle temperature	250 - 290	°C	-

Characteristics

Processing

Injection Molding

Applications

Automotive, IT / Business Machine, Electrical and Electronical

Delivery form

Black

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Increased electrical conductivity