

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
^[C] : CAMPUS			

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Stress at break	109	MPa	ISO 527
^[C] Strain at break	1.8	%	ISO 527
^[C] : CAMPUS			

Other properties	Value	Unit	Test Standard
^[C] Water absorption	0.08	%	Sim. to ISO 62
^[C] Density	1550	kg/m ³	ISO 1183
^[C] : CAMPUS			