

CELANEX® LX6402R

PBT-(GF+MD)40

Celanese

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	14600	MPa	ISO 527
^[C] Stress at break	140	MPa	ISO 527
^[C] Strain at break	1.8	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	201	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1720	kg/m ³	ISO 1183

[C]: CAMPUS