

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Stress at break	95	MPa	ISO 527
Strain at break	3	%	ISO 527
Flexural modulus, 23°C	11000	MPa	ISO 178
Flexural strength	155	MPa	ISO 178
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	180	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	200	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Other properties	Value	Unit	Test Standard
Density	1720	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	115 - 125	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.04	%	-
Melt temperature	235 - 265	°C	-
Mold temperature	60 - 95	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Features

Low Warpage

Chemical Resistance

General Chemical Resistance

Applications

Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific