

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	5000	MPa	ISO 527
Tensile Strength	55	MPa	ISO 527
Strain at break	4	%	ISO 527
Flexural modulus, 23°C	4500	MPa	ISO 178
Charpy impact strength, +23°C	45	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	2.5	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	M 70	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	185	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	95	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Dissipation factor, 1MHz	200	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	19	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	1590	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Features

Low Warpage

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa