

**LUPOX GP2156F**

PBT-GF15

LG Chem

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.007</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Break	<b>96.1</b>	MPa	ASTM D 638
Elongation at Break	<b>4</b>	%	ASTM D 638
Flexural Modulus	<b>5690</b>	MPa	ASTM D 790
Flexural Strength	<b>149</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>50.9</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>0.71</b>	mm	-
DTUL @ 66 psi	<b>210</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>200</b>	°C	ASTM D 648
Melting Temperature	<b>225</b>	°C	ASTM D 3418
<b>Electrical properties</b>			
<b>ISO Data</b>			
Comparative tracking index	<b>175</b>	-	IEC 60112
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>26</b>	kV/mm	ASTM D 149
Volume Resistivity	<b>1E17</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Density	<b>1520</b>	kg/m <sup>3</sup>	ASTM D 792
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	<b>120</b>	°C	-
Pre-drying - Time	<b>4 - 5</b>	h	-
Processing humidity	<b>≤0.02</b>	%	-
Melt temperature	<b>245 - 255</b>	°C	-
Mold temperature	<b>60 - 100</b>	°C	-
Zone 1	<b>235 - 250</b>	°C	-
Zone 2	<b>240 - 250</b>	°C	-
Zone 3	<b>245 - 255</b>	°C	-
Nozzle temperature	<b>245 - 255</b>	°C	-

**Characteristics****Processing**

Injection Molding

**Applications**

IT / Business Machine, Electrical and Electronical

**Special Characteristics**

Flame retardant

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America