

LUPOX GP2156FT

PBT-GF15

LG Chem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.007	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Break	98.1	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	5886	MPa	ASTM D 790
Flexural Strength	147	MPa	ASTM D 790
Izod Impact notched, 1/8 in	51.8	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.71	mm	-
DTUL @ 66 psi	210	°C	ASTM D 648
DTUL @ 264 psi	200	°C	ASTM D 648
Melting Temperature	225	°C	ASTM D 3418
Electrical properties			
ISO Data			
Comparative tracking index	175	-	IEC 60112
ASTM Data			
Dielectric Strength, Short Time	26	kV/mm	ASTM D 149
Volume Resistivity	1E17	Ohm*cm	ASTM D 257
Other properties			
Density	1520	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4 - 5	h	-
Processing humidity	≤0.02	%	-
Melt temperature	245 - 255	°C	-
Mold temperature	60 - 100	°C	-
Zone 1	235 - 250	°C	-
Zone 2	240 - 250	°C	-
Zone 3	245 - 255	°C	-
Nozzle temperature	245 - 255	°C	-

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant

Applications

IT / Business Machine, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific, South and Central America