

**NOVADURAN 5010GN2-15**

PBT-GF15

Mitsubishi Engineering-Plastics Corporation

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt volume-flow rate, MVR	48	cm <sup>3</sup> /10min	ISO 1133
Temperature	250	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Stress at break	110	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	6400	MPa	ISO 178
Flexural strength	167	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	224	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	193	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	214	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	26	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.7	-	IEC 62631-2-1
Dissipation factor, 1MHz	140	E-4	IEC 62631-2-1
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1
Surface resistivity	1E15	Ohm	IEC 62631-3-2
Electric strength	24	kV/mm	IEC 60243-1
Comparative tracking index	212	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	0.07	%	Sim. to ISO 62
Density	1540	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	5 - 8	h	-
Mold temperature	60 - 100	°C	-
Zone 1	250 - 270	°C	-
Zone 2	250 - 270	°C	-
Zone 3	250 - 270	°C	-
Nozzle temperature	270	°C	-
Screw speed	80 - 150	rpm	-
Injection pressure	20 - 150	MPa	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Applications**

Automotive, Electrical and Electronical, General Purpose

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa