

**Product Texts**

Vandar 4632Z is a high impact, 15% glass reinforced polyester alloy. It combines high strength and toughness with a moderate degree of rigidity. It is characterized by excellent solvent resistance, dimensional stability, and moldability.

Flammability at thickness h (1.5 HB mm)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	7	cm <sup>3</sup> /10min	ISO 1133
Temperature	250	°C	-
Load	5	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.3	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	4000	MPa	ISO 527
<sup>[C]</sup> Stress at break	60	MPa	ISO 527
<sup>[C]</sup> Strain at break	4	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	65	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	62	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	18	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	8	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	60	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	154	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	210	°C	ISO 75-1/-2
<sup>[C]</sup> Vicat softening temperature, B	180	°C	ISO 306
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	25	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	141	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	4.6	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	4.1	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	70	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	290	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	1E14	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	30	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.45	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	0.2	%	Sim. to ISO 62
<sup>[C]</sup> Density	1340	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Additives**

Lubricants

**Special Characteristics**

Heat stabilized or stable to heat

**Chemical Resistance**

Solvent Resistance

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information****Injection molding**

To avoid hydrolytic degradation during processing, Vandar resins have to be dried to a moisture level equal to or less than 0.02%.

Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for 4 hours.

Rear Temperature 450-480(230-250) deg F (deg C)

Center Temperature 460-490(235-255) deg F (deg C)

Front Temperature 470-500(240-260) deg F (deg C)

Nozzle Temperature 470-510(240-265) deg F (deg C)

Melt Temperature 470-510(240-265) deg F (deg C)

Mold Temperature 100-200(40-95 deg F (deg C)

Back Pressure 0-50 psi

Screw Speed Moderate

Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.