

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	8500	MPa	ISO 527
Stress at break	120	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Charpy impact strength, +23°C	60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	57	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	12	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	10	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	224	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	190	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	205	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	4	-	IEC 62631-2-1
Dissipation factor, 1MHz	170	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	27	kV/mm	IEC 60243-1
Comparative tracking index	300	-	IEC 60112

Other properties	Value	Unit	Test Standard
Humidity absorption	0.09	%	Sim. to ISO 62
Density	1660	kg/m <sup>3</sup>	ISO 1183

Test specimen production	Value	Unit	Test Standard
<b>ISO Data</b>			
Injection Molding, melt temperature	230	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

## Characteristics

### Processing

Injection Molding

### Regional Availability

Europe

### Delivery form

Pellets

## Other text information

### Injection Molding

PREPROCESSING

Max. Water Content 0,04%

Pre-Drying: 120°C 2-4 Hours

PROCESSING

Melt Temperature 240-260°C

Mould Temperature 80°C