

**Bergadur™ PB40 G20 UF UV**

PBT-GF20

Avient Corporation

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>17</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>250</b>	°C	-
Load	<b>1.6</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>6200</b>	MPa	ISO 527
Stress at break	<b>75</b>	MPa	ISO 527
Strain at break	<b>3</b>	%	ISO 527
Charpy impact strength, +23°C	<b>69</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>9.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>215</b>	°C	ISO 75-1/-2
<b>Electrical properties</b>			
<b>ISO Data</b>			
Comparative tracking index	<b>600</b>	-	IEC 60112
<b>Other properties</b>			
Density	<b>1520</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Pellets

**Regional Availability**

Europe, Near East/Africa

**Special Characteristics**

Flame retardant, Halogen-free, U.V. stabilized or stable to weather