

DURANEX® GFR320

PBT-GF20

Polyplastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	119	MPa	ISO 527
Strain at break	2.4	%	ISO 527
Flexural modulus, 23°C	7750	MPa	ISO 178
Flexural strength	179	MPa	ISO 178
Charpy notched impact strength, +23°C	6.1	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	205	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Yellow Card available	yes	-	-
Other properties			
Density	1620	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Additives

Flame retarding agent

Special Characteristics

Flame retardant, Heat stabilized or stable to heat

Certifications

Recycled Resin Content

Applications

Automotive, Electrical and Electronical

Regional Availability

Asia Pacific