

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>6600</b>	MPa	ISO 527
Tensile Strength	<b>95</b>	MPa	ISO 527
Strain at break	<b>3.1</b>	%	ISO 527
Flexural modulus, 23°C	<b>6300</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>57</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>8</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>207</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>220</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>50</b>	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Dissipation factor, 1MHz	<b>200</b>	E-4	IEC 62631-2-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1550</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics**

**Additives**

Flame retarding agent

**Special Characteristics**

Flame retardant, High impact or impact modified, Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa