

**Product Texts**

30% Glass Reinforced

ISO 1043 PBT-GF30

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	<b>18</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>250</b>	°C	-
Load	<b>2.16</b>	kg	-
<sup>[C]</sup> Density of melt	<b>1220</b>	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	<b>0.185</b>	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	<b>1850</b>	J/(kg K)	-
<sup>[C]</sup> Eff. thermal diffusivity	<b>8.23E-8</b>	m <sup>2</sup> /s	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>9750</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>145</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2.8</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>56</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>50</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>9.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>9.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>225</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>205</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>220</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>35</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>70</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>3.0</b>	mm	-
Yellow Card available	<b>yes</b>	-	-
<sup>[C]</sup> Burning rate, FMVSS, Thickness 1 mm	<b>55</b>	mm/min	ISO 3795 (FMVSS 302)
<sup>[C]</sup> Oxygen index	<b>20</b>	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	<b>3.9</b>	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	<b>3.7</b>	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	<b>25</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 1MHz	<b>170</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	<b>30</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>400</b>	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Water absorption	<b>0.3</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.15</b>	%	Sim. to ISO 62

---

[C] Density	<b>1510</b>	kg/m <sup>3</sup>	ISO 1183
-------------	-------------	-------------------	----------

---

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Additives**

Release agent

**Delivery form**

Pellets

**Regional Availability**

North America, Europe, Asia Pacific

**Other text information****Injection molding**[Injection Molding Recommendations](#)[Steel recommendations for molds screws and barrels](#)[Supporting document for Stanyl quality processing](#)