

## Product Texts

## ISO 7792-PBT, MGNR, 09-100, GF30

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste.

If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

**Crastin® SK615SF is a 30% glass fiber reinforced, low viscosity polybutylene terephthalate for injection molding. It has high flow characteristics and is specifically suitable for super fast production. It is laser markable.**

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melt volume-flow rate, MVR	19	cm <sup>3</sup> /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
<sup>[C]</sup> Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
<sup>[C]</sup> Density of melt	1360	kg/m <sup>3</sup>	-
<sup>[C]</sup> Thermal conductivity of melt	0.28	W/(m K)	-
<sup>[C]</sup> Spec. heat capacity of melt	1730	J/(kg K)	-
<sup>[C]</sup> Ejection temperature	170	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	9900	MPa	ISO 527
<sup>[C]</sup> Stress at break	145	MPa	ISO 527
<sup>[C]</sup> Strain at break	2.5	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	60	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	30	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	223	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	55	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	205	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	30	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	80	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
<sup>[C]</sup> Burning Behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
<sup>[C]</sup> Oxygen index	19	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Relative permittivity, 100Hz	4.1	-	IEC 62631-2-1
<sup>[C]</sup> Relative permittivity, 1MHz	3.9	-	IEC 62631-2-1
<sup>[C]</sup> Dissipation factor, 100Hz	20.6	E-4	IEC 62631-2-1

**Crastin® SK615SF NC010**

PBT-GF30

Celanese

<sup>[C]</sup> Dissipation factor, 1MHz	<b>173</b>	E-4	IEC 62631-2-1
<sup>[C]</sup> Volume resistivity	<b>&gt;1E13</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>1E14</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Electric strength	<b>39</b>	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	<b>375</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>0.35</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>0.15</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1530</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Processing**

Injection Molding

**Features**

Laser Markable

**Delivery form**

Pellets, Natural Color

**Regional Availability**

Europe, Asia Pacific

**Additives**

Release agent