

Product Texts

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® SK695FR is a 30% glass reinforced, flame retardant polybutylene terephthalate for injection moulding.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	3	cm ³ /10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
^[C] Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.1	%	ISO 294-4, 2577
^[C] Density of melt	1460	kg/m ³	-
^[C] Ejection temperature	170	°C	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11900	MPa	ISO 527
^[C] Stress at break	148	MPa	ISO 527
^[C] Strain at break	2.2	%	ISO 527
^[C] Charpy impact strength, +23°C	59	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	6.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	223	°C	ISO 11357-1/-3
^[C] Glass transition temperature, 10°C/min	55	°C	ISO 11357-1/-2
^[C] Temp. of deflection under load, 1.80 MPa	211	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-
^[C] Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	>1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	30	kV/mm	IEC 60243-1
^[C] Comparative tracking index	200	-	IEC 60112

[C]: CAMPUS

Crastin® SK695FR BK507

PBT-GF30 FR(17)

Celanese

Other properties	Value	Unit	Test Standard
^[C] Density	1670	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Flame retardant

Delivery form

Pellets, Black

Regional Availability

North America, Europe, Asia Pacific, South and Central America