

MAXNITE 550 GF30

PBT-GF30

MRC Polymers, Inc.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	130	MPa	ISO 527
Flexural modulus, 23°C	8500	MPa	ISO 178
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	190	°C	ISO 75-1/-2
Other properties			
Density	1520	kg/m ³	ISO 1183

Characteristics**Delivery form**

Black

Applications

Automotive

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America