

NEVIESTER B1 V30

PBT-GF30

Nevicolor S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.3	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	9000	MPa	ISO 527
Stress at break	130	MPa	ISO 527
Strain at break	2	%	ISO 527
Flexural modulus, 23°C	8500	MPa	ISO 178
Izod impact strength, +23°C	40	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	200	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	215	°C	ISO 75-1/-2
Vicat softening temperature, A	220	°C	ISO 306
Vicat softening temperature, B	210	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Other properties			
Value			
Humidity absorption	0.15	%	Sim. to ISO 62
Density	1530	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe