

**NIBLAN F30**

PBT-GF30

Soredi S.p.a.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	22	g/10min	ASTM D 1238
Temperature	250	°C	-
Load	2.16	kg	-
Mold Shrinkage, MD	0.007	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Break	110	MPa	ASTM D 638
Flexural Modulus	6000	MPa	ASTM D 790
Flexural Strength	180	MPa	ASTM D 790
Rockwell Hardness	M 85	-	ASTM D 785
Izod Impact notched, 1/8 in	57.6	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	43.2	J/m	ASTM D 256
Temperature	-22	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Coeff. of linear therm. expansion, normal	30	E-6/K	ISO 11359-1/-2
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 264 psi	215	°C	ASTM D 648
Melting Temperature	220	°C	ASTM D 3418
<b>Electrical properties</b>			
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.7	-	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	35	kV/mm	IEC 60243-1
<b>Other properties</b>			
Water Absorption, 24hr	0.4	%	ASTM D 570
Density	1440	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Delivery form**

Natural Color

**Regional Availability**

Europe