

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	10000	MPa	ISO 527
Stress at break	130	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Charpy impact strength, +23°C	50	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	8	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
Izod notched impact strength	7	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	210	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Vicat softening temperature, B	210	°C	ISO 306
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.6	mm	-
Electrical properties			
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2
Comparative tracking index	225	-	IEC 60112
Other properties			
Water absorption	0.3	%	Sim. to ISO 62
Humidity absorption	0.1	%	Sim. to ISO 62
Density	1640	kg/m ³	ISO 1183

Characteristics

Special Characteristics

Flame retardant, High impact or impact modified, U.V. stabilized or stable to weather

Features

Thermal Stability

Chemical Resistance

General Chemical Resistance

Applications

Electrical and Electronical

Regional Availability

Europe