

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	30	cm ³ /10min	ISO 1133
Temperature	260	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9800	MPa	ISO 527
^[C] Stress at break	120	MPa	ISO 527
^[C] Strain at break	2.6	%	ISO 527

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	207	°C	ISO 75-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Comparative tracking index	600	-	IEC 60112

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1530	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Certifications

Recycled Resin Content

Regional Availability

North America, Europe, Asia Pacific