

**PRECITE® P1 GF 30 natural (7062)**

PBT-GF30

Akro-Plastic GmbH

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>9800</b>	MPa	ISO 527
Stress at break	<b>150</b>	MPa	ISO 527
Strain at break	<b>3.1</b>	%	ISO 527
Charpy impact strength, +23°C	<b>75</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>11</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Burning behav. at thickness h	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8</b>	mm	-
<b>Other properties</b>			
Density	<b>1530</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Natural Color

**Applications**

Automotive, Electrical and Electronical

**Chemical Resistance**

General Chemical Resistance

**Regional Availability**

Europe, Asia Pacific