

PTS PBT-30GF(V)

PBT-GF30

Amco Polymers

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	110	MPa	ASTM D 638
Flexural Modulus	7584	MPa	ASTM D 790
Rockwell Hardness	R 118	-	ASTM D 785
Izod Impact notched, 1/8 in	80.1	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.52	mm	-
DTUL @ 264 psi	204	°C	ASTM D 648

Characteristics**Delivery form**

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Special Characteristics

U.V. stabilized or stable to weather